

Date: 20100701					
Name of test spinner: David Taylor Daniels					
Email Address of test spinner: davidtdaniels@gmail.com					
Fiber Name:	Silver Gray 100% Corriedale (2008/2009 fleece) – Ulf	Brown 100% Corriedale (2008/2009 fleece) – Ukulele	Medium Gray Corriedale/Columbia /Romney X Shetland	Ivory Corriedale/Columbia /Romney X Shetland	Lt Gray/Tan Corriedale/Columbia /Romney X Shetland
Quantity	1 ounce	1 ounce	1 ounce	1 ounce	1 ounce
Spinning method – Wheel (type:) or Hand Spindle (type and weight:)	Schacht Single Treadle Wheel	Schacht Single Treadle Wheel	Schacht Single Treadle Wheel	Schacht Single Treadle Wheel	Schacht Single Treadle Wheel
Direction spun –					
Singles: S or Z	S	S	S	S	S
Plying: S or Z	Z	Z	Z	Z	Z
How many plies?	2	2	2	2	2
Wraps per inch:	18	18	16	16	16
Yards of finished yarn:	78	72	54	52	50
Yarn category:					
Method of spinning: Worsted - Semi-worsted - woolen (long draw) - I don't know, I just spin	Worsted	Worsted	Worsted	Worsted	Worsted
How clean was this fiber (well washed? Lots of vegetation? Some vegetation?)	Very clean	Very clean	Very clean	Very clean	Very clean
How easy/hard was it to draft and spin?	Easy to spin	Easy to spin	Easy to spin	Easy to spin	Easy to spin
What is this fiber's best and worst features? Best:	Beautiful finished yarn	Creates a nice dense yarn	Creates a nice dense yarn	Easy to spin, blooms well after washing	Makes a beautiful yarn, a nice halo on finished yarn
Worst:	None	None	Very coarse fiber, but nice yarn	None	None
Suggested uses for spun yarn:					
Would you recommend this fiber to other spinners? Y or N Why?	Yes	Yes	Yes	Yes	Yes
Notes:					